


THAI FILM INDUSTRIES PUBLIC CO., LTD.

C-24



CPP CO-EX NORMAL HEAT SEAL FILM

Description:

This film is widely used in packaging printing and laminating application. Available for one side treatment and non treatment.

Characteristics:

Clarity

Suitable for printing and heat sealing Uniform and stable sealing strength

TECHNICAL DATA

TECHNICAL DATA										
TYPICAL PROPERTIES	UNIT		TEST METHODS	TYPICAL VALUE						
THICKNESS	Micron		Progage	18	20	25	30	35	40	50
YIELD	m²/kg		-	61.05	54.95	43.96	36.63	31.40	27.47	21.98
DENSITY	g/cm³		ASTM D-1505	0.91						
AVERAGE THICKNESS VARIATION	%		ASTM E-252	± 3						
TENSILE STRENGTH	kg/mm² (min)	MD TD	ASTM D-882	4 2						
ELONGATION AT BREAK	% (min) MD TD		ASTM D-882	400 400						
KINETIC C.O.F.	NT/NT		ASTM D-1894	0.6 - 0.9						
WETTING TENSION	Dyne/cm (min)		ASTM D-2578	38						
SEALING TEMPERATURE	°C (min)		1 BAR 1 SEC	120						
SEALING STRENGTH	g/15mm (min)		-	500	00 600 800					
GLOSS (Angle 45°)	% (min)		ASTM D-2457	75						
HAZE	% (max)		ASTM D-1003	3.5			4	.0	5.0	5.5
WVTR (38 ℃, 90% RH)	g/m²/24hr (max)		ASTM F-1249	14	13	12	9	8	7	5
O ₂ TR (23 °C, 0% RH)	cc/m²/24hr (max)		ASTM D-3985	4100	3800	3000	2600	2200	1900	1200

DESCRIPTION OF SUPPLY

PAPER CORE I.D. 77 mm (3 in.) 153 mm (6 in.)

ROLL O.D. max. 800 mm

WIDTH RANGE 100 mm - 2,000 mm. (other width on request), Allowance 0, +3 mm

COMBINATION WIDTH 2.350 mm.

LENGTH RANGE STANDARD 4,000 m., 6,000 m. (other length on request)

JOINT maximum 10% per order

Food approval: Complied with US FDA & EU regulations (on request).

Storage condition: Should be kept in dry storage with temperature 30°C - 40°C.

Disclaimer:

The information provided above is accurate to the best of our knowledge. It is however suggested that the customer confirms these values and product compatibility prior to their use. Thai Film Industries PCL offers no guarantees nor accepts any responsibility for the fitness of the product for any particular use. 14/03/2016